

FENWICK & TILBROOK

THE PAINT AND COLOUR EXPERTS

Application

Pure Matt Plus

3% Sheen Flat Matt Finish

DESCRIPTION

A highly durable, water based pure finish matt (3%) emulsion available in the full F&T palette, designed for interior use on plaster walls and ceilings, prepared wood and primed metal. The low VOC water-based formulation is ideally suited to high traffic areas, retaining a durable, washable finish with extraordinary depth of colour.

PROPERTIES

- Outstanding durability
- Extraordinary depth of colour
- Ease of application
- Great coverage
- Extremely low odour
- Very low VOC content.

APPLICATION NOTES:

Stir thoroughly before use. Apply two coats Fenwick & Tilbrook paint by brush, roller or spray application. If light or bright colours are to be used an additional coat may be required. Tones of separate batches may vary slightly, for colour consistency purchase enough paint for the complete job at one time.

PREPARATION

Preparation of the surface to be painted is vital to the performance of your F&T paint.

- Make good any structural cracks or defects and match the finish to the existing substrate. Use flexible fillers only.
- Wash down and remove old flaking or defective coating.
- A glossy painted surface must be sanded to a matt finish prior to applying the first coat of Fenwick & Tilbrook paint. Avoid the inhalation of dust. Wear a suitable face mask when dry sanding.
- Bare metal requires a suitable primer.

- Fenwick & Tilbrook paints are self-priming, however if a heavily repaired substrate has a wide variation of porosity and colours, priming is recommended as a first coat to create an even base colour.
- For interior use, prime new, bare and porous surfaces using one coat of the appropriate F&T paint, thinned with water (1-part water, 9 parts paint).
- For new plaster first apply an appropriate mist-coat to ensure a good bond can be achieved.

COVERAGE

Coverage approximately 10m² per litre.

DRYING TIMES

Touch dry in 30 minutes, recoatable after two hours. Allow longer in cool or damp conditions. (Do not apply at temperatures below 5°C). Interval between coats c.1 hour. *Based on 23°C ambient temperature, 50% relative humidity, 50-micron dry film thickness (DFT). Temperature, humidity and thickness of coat will affect drying times.*

APPLICATION METHODS

Suitable for application by brush, roller or airless spray.

PRIMING

Fenwick & Tilbrook paints are self-priming. However, if a heavily repaired substrate has a variation of porosity and colours, priming is recommended as a first coat to create an even base colour. Prime new, bare and porous surfaces by using one coat of Fenwick & Tilbrook paint thinned with water (one-part water, nine parts paint).

CLEAN UP

Remove as much product as possible from brushes and equipment before cleaning with warm water. Do not empty into drains or watercourses. Some local authorities have special facilities for the disposal of waste coatings.

STORAGE AND STABILITY

Store upright in dry conditions above 5°C. Protect from frost. To avoid risk of spillage, always store and transport in a secure, upright position.